

Femtosecond dynamics of long-range order: coupling of the lattice, spins, charge and orbitals



Steve Johnson

ETH Zurich



- Overview: dynamics as pathway to control
- X-rays as a selective probe of structure in condensed matter
- Indirect control: coupled lattice, orbital and charge in PCMO
 - Aside: a first look at x-ray “control” in a solid
- Direct control: coherent electromagnon in TbMnO₃
- Outlook

Structure and function



Graphite



Diamond


Conventional: adiabatic/stochastic




Temperature, pressure, static fields...
...works, but slow.

Can we do this faster, more efficiently?

Dynamics of symmetry changes




[Doiron-Leyraud et al. Nature 447, 565 (2007)]



[Hwang et al. PRB 52, 15046 (1995)]



Equilibrium thermodynamics powerful: Critical phenomena, RG theory



Time scales \approx interaction times
($\sim 1-1000$ fs): breakdown of
conventional thermodynamics





Experimental concept

Intense **light pulses** to **perturb structure**




+

Femtosecond-resolved **x-ray** probes of structure changes




Understand & control of atomic-scale structural dynamics

Light as a control knob




- Mature technology for creating / shaping pulses at near-optical frequencies
- Recent advances at lower frequencies make direct resonant excitation of IR active modes possible

X-ray pulses as a fast probe




- X-ray diffraction: access to long-range atomic-scale order
- Sources for short pulses
 - Electron-beam slicing at Swiss Light Source (PSI)
 - X-ray free electron lasers



X-ray pulses as a fast probe

- Non-resonant: first-order elastic scattering dominated by $|A|^2$ term in H_{int}
- Intensity related to FT of electron density




$$H_{\text{int}} = -\frac{q}{mc}(\mathbf{A} \cdot \mathbf{P} + \mathbf{P} \cdot \mathbf{A}) + \frac{q^2 |\mathbf{A}|^2}{2mc^2}$$

(non-relativistic, spin ignored)

$$I(Q) \propto |F(Q)|^2 = \left| \sum_j f_j e^{i\mathbf{r}_j \cdot \mathbf{Q}} \right|^2$$

X-ray pulses as a fast probe

- Near core-level resonance: large second-order scattering
- Enhanced contributions from valence states




$$H_{\text{int}} = -\frac{q}{mc} (\mathbf{A} \cdot \mathbf{P} + \mathbf{P} \cdot \mathbf{A}) + \frac{q^2 |\mathbf{A}|^2}{2mc^2}$$

$$\Delta f = \sum_j \frac{\langle \psi_i | H_{\text{int}} | \psi_j \rangle \langle \psi_j | H_{\text{int}} | \psi_i \rangle}{h\omega - (E_j - E_i) + i\Gamma/2}$$


“Indirect” vs. “Direct” control

Bismuth



[Zijlstra, Tatarinova & Garcia, PRB 74, 220301 (2006)]

TbMnO₃




[Kida et al., JOSAB 26 A35 (2009)]




- “Indirect” control of order parameters
 - Excitation of other DOF, couples to order
- “Direct” control
 - Drive order directly with EM pulse

“Indirect” control: Electronically induced structure changes


- Distorted perovskite
- Charge and orbital ordering below 240 K
- Strong lattice distortion due to Jahn-Teller interaction




- CE-type charge & orbital order
- Jahn-Teller distortion at Mn³⁺ sites doubles unit cell



$T > T_{CO/OO}$
orthorhombic $Pbnm$




$T < T_{CO/OO}$
monoclinic $P2_1/m$



● Mn³⁺ ● Mn⁴⁺ ● O ● Pr/Ca

- Photoexcitation: perturbation of charge and orbitals
- Forces system to higher symmetry state
- How does this couple to structure?



Experiment team: $\text{Pr}_{0.5}\text{Ca}_{0.5}\text{MnO}_3$



P. Beaud
U. Staub
S.-W. Huang
J. Johnson
C. Vicario
G. Ingold

S. Gruebel
S. Mariager
L. Patthey

SLAC:


J. Glowia
H. Lemke
M. Chollet
A. Robert
D. Fritz
D. Zhu

ETHZ:

A. T. Huber
A. Ferrer
T. Kubacka
L. Huber
C. Dornes
V. Scagnoli

RIKEN/U. Tokyo:


M. Nakamura
H. Wadati
M. Kawasaki
Y. Tokura



SWISS NATIONAL SCIENCE FOUNDATION

Experiment

- 40 nm film sample of $\text{Pr}_{0.5}\text{Ca}_{0.5}\text{MnO}_3$
- $(011)_c$ orientation
- Pumped at 1.55 eV, 50 fs pulses
- Probed with ~ 6.55 keV, ~ 50 fs
- Cornell-SLAC Pixel Array Detector



Resonant diffraction at Mn K-edge





- From hybridization of Mn 3d and O 2p states
[Zimmermann et al. PRL 83, 4871 (1999)]

for k odd...

(h k/2 0): structural distortion


(0 k/2 0): orbital order & Jahn-Teller

(0 k 0): charge order






Resonant diffraction at Mn K-edge

- From hybridization of Mn 3d and O 2p states
[Zimmermann et al. PRL 83, 4871 (1999)]




Time resolution

- Per-shot arrival time monitor essential [spectral encoding method, Harmand et al. Nat. Photon. 7, 215 (2013)]
- Dramatic improvement over previous measurements



[P. Beaud et al., Nature Mater. 13, 923 (2014)]

Overview: coupled motions




- Different reflections in & out of resonance gives access to different types of long-range order
- Above a certain excitation density, all go to zero at $t > 1$ ps
- Charge order melting fastest
- Other peaks see strong coherent vibration contribution

[P. Beaud et al., Nature Mater. 13, 923 (2014)]

“Time-dependent” order parameter


- Use (0 -3 0) intensity as a measure of charge order
- Intensity gives square of Mn charge modulation amplitude
- Identify charge modulation amplitude as a transient order parameter η_t
- Order parameter varies with time (and depth)



[P. Beaud et al., Nature Mater. 13, 923 (2014)]

“Time-dependent” order parameter

(0 -3 0) at t = 250-500 fs



- Early time excitation fluence dependence well described by

$$\eta_t = \begin{cases} \sqrt{1 - \frac{n_0}{n_c}} & n_0 < n_c \\ 0 & n_0 \geq n_c \end{cases}$$


n_0 = initial electronic energy density, proportional to fluence

n_c = 350 meV/Mn site

- Very similar to Landau mean-field result for 2nd order phase transitions

[P. Beaud et al., Nature Mater. 13, 923 (2014)]

Time evolution of order parameter




- Later times, after e-ph interaction:

$$\eta_t(t_{\text{late}}) = \left(1 - \frac{n_0}{n_c}\right)^\gamma \quad \gamma = 0.20 \pm 0.02$$

Change of exponent: onset of long-range correlations?

[P. Beaud et al., Nature Mater. 13, 923 (2014)]

Time evolution of order parameter



- Represent as an evolving $n(t)$:

$$\eta_t = \begin{cases} \sqrt{1 - \frac{n}{n_c}} & n < n_c \\ 0 & n \geq n_c \end{cases} \quad n(t) = (n_0 - an_c)e^{-t/\tau} + an_c$$


$$a = 1 - \left(1 - \frac{n_0}{n_c}\right)^{2\gamma}$$

[P. Beaud et al., Nature Mater. 13, 923 (2014)]

- Coupling to structure via a time-dependent interatomic potential
- For quasi 1-D systems with one transition coordinate, Landau form has worked


[Yusupov et al. Nat. Phys. 6, 681 (2010)]

[Huber et al. Phys. Rev. Lett. 113, 026401 (2014)]



$$V(x, t) = V_0 + a [n(t) - n_c] x^2 + bx^4$$


Coupled dynamics of structure



- In PCMO, multiple independent vibrational modes contribute
- Simplify as only four groups of modes


$$V(y_1, y_2, y_3, y_4, t) = V_0 + \underbrace{a[n(t) - n_c] y_1^2 + b y_1^4}_{\text{driven motion}} + \underbrace{c_{21}(y_2 - y_1)^2 + c_{32}(y_3 - y_2)^2 + c_{43}(y_4 - y_3)^2}_{\text{chain of coupled motions}}$$

Coupled dynamics of structure



- Use time-dependent potential to construct equations of motion (linear damping added)


[P. Beaud et al., Nature Mater. 13, 923 (2014)]



- Strong coupling: lowest frequency dominates at late times
- High fluence: overshoot of high symmetry point leads to doubling in measured diffraction signal

[P. Beaud et al., Nature Mater. 13, 923 (2014)]

Aside: X-rays as driver?



- X-ray pump to drive electronic and possible structural motion (tuned to diffraction peak)
- Detection channel: change in polarization of transmitted optical light

[A. Ferrer et al., Appl. Phys. Lett. 106, 154101 (2015)]

Experiment team: ZnO

ETHZ:

A. Ferrer
T. Huber
V. Scagnoli
M. Trant


SLAC:

D. Zhu
M. Chollet
H. T. Lemke




J. A. Johnson
U. Staub
S. O. Mariager
G. Ingold

C. Milne
S. Gruebel
P. Beaud
L. Patthey



SWISS NATIONAL SCIENCE FOUNDATION

Persistent induced anisotropy




- Nonlinear increase in optical anisotropy from electronic excitation
- Delayed onset, signal persists to ~ 6 ps!!

[A. Ferrer et al., Appl. Phys. Lett. 106, 154101 (2015)]


“Indirect” vs. “Direct” control

Bismuth



[Zijlstra, Tatarinova & Garcia, PRB 74, 220301 (2006)]

TbMnO₃




[Kida et al., JOSAB 26 A35 (2009)]

- Indirect works, but some significant disadvantages:
 - Competing channels (especially for electronic excitation)
 - Upscaling limited in potential
 - Often irreversible

“Direct” control: Resonant THz excitations


THz excitation: path to fast control of multiferroics?




excitations due to the electromagnetic coupling:

higher-harmonic, ellipticity, phonons
0.7 THz

spin-spiral excitation,
1.8 THz




[Y. Takahashi et al., PRL **101**, 187201 (2008)]




[Mochizuki & Nagaosa, PRL **105**, 147202 (2010)]

Experiment concept




Pump electromagnon with THz, watch spins with resonant x-ray diffraction

X-ray pulses: probe spin order



- (0q0) reflection at Mn L-edges: only magnetic order

$$\langle \mathbf{T}_q^k \rangle \propto \sum_n \frac{\langle g | O | n \rangle \langle n | O^* | g \rangle}{E_n - E_g - \hbar\omega + i\Gamma}$$



- Experiment at LCLS
- Pulses of < 80 fs duration
- Time-stamping for < 250 fs resolution



[Beye et al. Appl. Phys. Lett. 100, 121108 (2012)]

Experiment team: TbMnO₃

ETHZ:

T. Kubacka
L. Huber
V. Scagnoli

SLAC:

M. Hoffmann
S. de Jong
J. Turner
W. Schlotter
G. Dakovski

LBL:


Y.-D. Chuang

Stanford:

W.-S. Lee
R. G. Moore

Johns Hopkins:

S. M. Koohpayeh



U. Staub
S.-W. Huang
J. Johnson
C. Vicario
G. Ingold



Ch. Hauri
S. Gruebel
P. Beaud
L. Patthey



SWISS NATIONAL SCIENCE FOUNDATION

Results: coherent electromagnon


- E-field of THz \rightarrow coherent spin response
- Measured spin response delayed by half cycle
- Response suppressed in non-multiferroic phase





[T. Kubacka et al., Science **343**, 1333 (2014)]

Analyzing the motion

In-plane rotation




Rotation of spin planes



$\Rightarrow 4.2 \pm 0.4$ degree rotation of spin planes


[T. Kubacka et al., Science **343**, 1333 (2014)]

Analyzing the motion



- What about time response?
- Approximate electromagnons as damped harmonic oscillators


Analyzing the motion



- Susceptibility vs. frequency: phase lag of 90 degrees at resonance
- ...but data shows lag of 180 degrees!?!

Analyzing the motion


$$\begin{aligned}
 H = & \sum_{\langle i,j \rangle} J_{ij} \mathbf{S}_i \cdot \mathbf{S}_j + D \sum_i S_{\zeta i}^2 + E \sum_i (-1)^{i_x + i_y} (S_{\zeta i}^2 - S_{\eta i}^2) \\
 & + \sum_{\langle i,j \rangle} \mathbf{d}_{ij} \cdot (\mathbf{S}_i \times \mathbf{S}_j) - B_{\text{biq}} \sum_{\langle i,j \rangle}^{ab} (\mathbf{S}_i \cdot \mathbf{S}_j)^2
 \end{aligned}$$



- Dynamics dominated by spin interaction
- One component of spin motion (in-plane) coupled to polarization
- No “kinetic energy”: role of momentum played by another spin component (similar to precession)

[Michizuki & Nagaosa, Phys. Rev Lett. 105, 147202 (2010)]


Analyzing the motion



- X-ray response corresponds to the “momentum” of a harmonic oscillator driven by E-field
- Rotation of spin planes fills this role

[T. Kubacka et al., Science **343**, 1333 (2014)]

Analyzing the motion







- Similar analysis assuming lower-frequency resonance is poorer match to data

[T. Kubacka et al., Science **343**, 1333 (2014)]

Summary

- Indirect control via e-ph coupling
 - Entropy in electron system couples to other DOFs
- Direct control with THz
 - Drive spin structure changes with E-field, switching expected at ~ 10 MV/cm





[Calculations from M. Savoini]

- Way forward: micro-antennas
 - Enhancement factors of > 10 with large volumes

ETH UDG Group (January 2015)

